

K600



SCHEDA TECNICA TECHNICAL DATA SHEET

	Analisi chimica <i>Chemical analysis</i>	SiO ₂ Al ₂ O ₃ + ZrO ₂ Fe ₂ O ₃ + TiO ₂ CaO + K ₂ O + Na ₂ O	17-19% 80-82% 1-2% <1%
	Analisi mineralogica <i>Crystallographic analysis</i>		MULLITE CORUNDUM BADDELEYITE
	Modulo di rottura <i>Modulus of rupture</i>		450 ± 50 Kg/cm ²
	Modulo di elasticità <i>Modulus of elasticity</i>		80 – 95 GPa
	Assorbimento d'acqua <i>Water absorption</i>		6.5 – 7.5 %
	Densità apparente <i>Bulk density</i>		2.7 – 2.8 g/cm ³
	Porosità apparente <i>Apparent porosity</i>		19.0 – 22.0%
	Coeff. di espansione termica (1000°C) <i>Thermal expansion coefficient (1000°C)</i>		5.9 – 6.3 x10 ⁻⁶ /K
	Resistenza allo sbalzo termico <i>Thermal shock resistance</i>		Very Good
	Massima temperatura di utilizzo <i>Max suggested working temperature</i>		1220°C

I dati riportati sono ottenuti dai test di laboratorio sul prodotto finito e non forniscono alcuna garanzia.
The technical data are obtained from laboratory tests on production and they give no guarantee.

Date of rev. 15/07/2024